



plavshpat.com

### Fluorspar concentrate lump / briquette

Sample name	CaF <sub>2</sub> (%)	CaCO <sub>3</sub> (%)	SiO <sub>2</sub> (%)	P (%)	S (%)	W (H <sub>2</sub> O) (%)
FB-85	85,4	1,7	3,58	0,018	0,037	2
lump size, mm	%					
50 x 50 x 30	>95					
-10	<5					