



plavshpat.com

Fluorspar concentrate

Sample name	CaF ₂ (%)	CaCO ₃ (%)	SiO ₂ (%)	P (%)	S (%)	As (г/т)	H ₂ O 110 C, %
FF-95A	95,62	1,47	1,17	0,02	0,02	<30	0,03
particle size, мм	%						
+0,14	3						
-0,14	83						
+0,063	14						